



PARSHWANATH
DYESTUFF INDUSTRIES

AN ISO 9001 & 14001 CERTIFIED COMPANY

DIRECT DYES

Textile | Paper | Jute | Velvet | Coir



COMPANY PROFILE

PARSHWANATH GROUP OF INDUSTRIES was incorporated in 1998 as a small-scale reactive dyes manufacturing unit. Today, Parswanath group has emerged as a leading business conglomerate in [Reactive dyes](#), [Food Color](#), [Lake Food Color](#), [Acid dyes](#), [Direct dyes](#), [Solvent Dyes](#), [Pigment Powder and Pigment Emulsion](#) industry, It's our experience that has enabled us to develop and maintain "State of Art" Infrastructure. Our company has been called, "The company with a good attitude".

We are offering our services to enabled our principal to reach the destination where they can perform effectively and [face any type of competitive business market](#) to attain their targets. With a strong vision of corporate governance, business ethics and customer satisfaction, we are growing from strength to strength. Parshwanath Group of Industries is structured around classic organization department such as sales, operations, marketing, finance, etc. with a strong belief in fundamental proven business practices. At the same time, our group has implemented unique and progressive conduct environment of management control system.



PARSHWANATH DYESTUFF INDUSTRIES

(UNIT OF REACTIVE DYES)

Plot No. I/5617, Phase-2, G.I.D.C., Vatva, Ahmedabad-382445. INDIA

P : +91-79-4008 3230, 4008 3231

M : +91 990 990 3636, 997 987 4744

E : inquiry@parshwadyes.com, sonal.modi@parshwadyes.com

W : www.parshwadyes.com



PARSHWANATH COLOUR CHEM.

(UNIT OF FOOD COLOUR)

PLOT NO. 452/453, PHASE-II, VATVA G.I.D.C., AHMEDABAD-382 445. INDIA



SHUBHLAMXI INDUSTRIES

(UNIT OF DYES INTERMEDIATE)

Plot No.443, Phase -2, G.I.D.C., Vatva, Ahmedabad - 382445, INDIA



SHANGHAI COLOUR CHEM

(UNIT OF ACID DYES & DIRECT DYES)

NO. C-1/88/5, PHASE-I, G.I.D.C., VATVA, AHMEDABAD - 382 445. (INDIA)



RUSHVI FINE CHEM PVT. LTD.

(UNIT OF PIGMENT EMULSION & PIGMENT POWDER)

A/2/481-482, PHASE-II, G.I.D.C., VATVA, AHMEDABAD - 382 445. (INDIA)



COTTON

0.5%

2%

Product Name
(N.B.)

Fastness Properties

Light	Washing	Perspiration	Hypochlorite	Dischargeability
-------	---------	--------------	--------------	------------------

	DIRECT YELLOW 3GX DIRECT YELLOW 6	4	3	2-3	3	3-4
	DIRECT YELLOW CFG DIRECT YELLOW 8	5	4-5	4-5	5	4-5
	DIRECT PAPER YELLOW T DIRECT YELLOW 11	4	3-4	3-4	3	3-4
	DIRECT FAST YELLOW RR DIRECT YELLOW 28	5	4-5	4-5	3-4	4-5
	DIRECT YELLOW 3RL DIRECT YELLOW 34	5	4-5	4-5	3-4	4-5
	DIRECT YELLOW 5GLL DIRECT YELLOW 44	5	3	4-5	5	4-5
	DIRECT YELLOW RLL DIRECT YELLOW 50	6	4-5	4-5	3-4	4-5
	DIRECT YELLOW 2RLX DIRECT YELLOW 86	5	4-5	4-5	3-4	4-5
	DIRECT SUN YELLOW RCH DIRECT YELLOW 99	4	2-3	4	4	3-4
	DIRECT YELLOW G DIRECT YELLOW 107	5	3	4-5	5	4-5
	DIRECT YELLOW PG DIRECT YELLOW 142	5-6	4	4-4	3	4-5
	DIRECT ORANGE SE DIRECT ORANGE 26	2-3	3	4-5	3	4
	DIRECT ORANGE GLL DIRECT ORANGE 39	6-7	4-5	5	3	4-5
	DIRECT VISCOSE ORANGE A DIRECT ORANGE 108	6	4-5	5	2-3	4-5
	DIRECT BRILLIANT FAST VIOLET 2RL DIRECT VIOLET 7	6	2-3	4-5	2-3	4



COTTON

0.5%

2%

Product Name
(N.B.)

Fastness Properties

Light	Washing	Perspiration	Hypochlorite	Dischargeability



DIRECT BRILLIANT VIOLET NB
DIRECT VIOLET 9

2-3 2-3 2 5 4



DIRECT PAPER VIOLET BL
DIRECT VIOLET 35

5 2-3 2 4-5 4



DIRECT BRILLIANT FAST HELIO B
DIRECT VIOLET 51

4 2-3 2 4-5 4-5



DIRECT VIOLET 4BLL
DIRECT VIOLET 66

4 3 3 5 4-5



DIRECT SKY BLUE FB
DIRECT BLUE 1

5 4-5 4-5 2-3 2



DIRECT BLUE G
DIRECT BLUE 8

4 3-4 3-4 5 2



DIRECT SKY BLUE FF
DIRECT BLUE 15

2 3 3 4-5 4-5



DIRECT BLUE NB
DIRECT BLUE 54

5 4-5 4-5 2-3 4



DIRECT LIGHT FAST BLUE GL
DIRECT BLUE 71

5 4-5 4-5 2-3 1-2R



DIRECT BLUE 2RLL
DIRECT BLUE 80

5 4 4-5 3-4 2R



DIRECT TURQ BLUE GL
DIRECT BLUE 86

6 4 3 3 3Y



DIRECT COPPER BLUE 2R
DIRECT BLUE 151

5 4 4-5 3-4 2



DIRECT TURQ BLUE FBL
DIRECT BLUE 199

6 4-5 5 2-3 2Y



DIRECT SUPRA BLUE BRL
DIRECT BLUE 201

6 4-5 4-5 2-3 3Y



DIRECT LIGHT BLUE 5GLL
DIRECT BLUE 218

4-5 4 4-5 3-4 2



COTTON		Product Name (N.B.)	Fastness Properties				
			Light	Washing	Perspiration	Hypochlorite	Dischargeability
0.5%	2%	DIRECT BROWN DL4R DIRECT BROWN 78	4	3-4	3-4	2-3	4
		DIRECT BROWN BRLL DIRECT BROWN 95	4-5	4-5	4-5	3-4	4
		DIRECT BROWN GTL DIRECT BROWN 210	5-6	4-5	4-5	3-4	3Y
		DIRECT BORDEAUX 6B DIRECT RED 16	4	3-4	4	4-5	4-5
		DIRECT FAST SCARLET 4BS DIRECT RED 23	3	3-4	3	4	4
		DIRECT RED 12B DIRECT RED 31	3	3	2-3	3	3-4
		DIRECT PINK 2B DIRECT RED 75	5	4	4	5	4
		DIRECT SOLOPHENYL RED 6BL DIRECT RED 79	6	4	4	5	4
		DIRECT SOLOPHENYL RED 3BL DIRECT RED 80	5	3-4	4	4	4
		DIRECT RED 5BL DIRECT RED 81	5	3	1-2	5	4-5
		DIRECT RUBINE 2RL DIRECT RED 83	6	4-5	5	2	2Y
		DIRECT RED GR2 DIRECT RED 111	4-5	5	4	4-5	4
		DIRECT FAST ROSE FR DIRECT RED 227	3-4	4-5	4-5	2	1Y
		DIRECT SCARLET 4BNX DIRECT RED 239	3	3-4	4	4-5	4-5
		DIRECT FAST RED BFX DIRECT RED 254	4	3-4	4	4-5	4-5



COTTON		Product Name (N.B.)	Fastness Properties				
			Light	Washing	Perspiration	Hypochlorite	Dischargeability
0.5%	2%	DIRECT GREEN 2BN DIRECT GREEN 96	4	3-4	4	4-5	4
		DIRECT GREEN NBX DIRECT GREEN 114	4	3-4	4	4-5	4
		DIRECT FAST BLACK G DIRECT BLACK 19	3-4	4	4-5	3	2YR
		DIRECT BLACK VSF DIRECT BLACK 22 (600%)	4-5	4R	4-5	2-3	2YR
		DIRECT BLACK VSF DIRECT BLACK 22 (1600%)	4-5	4R	4-5	2-3	2YR
		DIRECT GREY L DIRECT BLACK 51	5	4-5	4-5	2-3	1-2R
		DIRECT BLACK OBN DIRECT BLACK 80	2-3	4	4-5	3	1-2R
		DIRECT BLACK BF DIRECT BLACK 155	3	3-4	4-5	4	4
		DIRECT BLACK SGR DIRECT BLACK 168 (REDDER)	5	4-5	4-5	2-3	3Y
		DIRECT BLACK SBG DIRECT BLACK 168 (GREENER)	5	4-5	4-5	2-3	3Y
		DIRECT BLACK ESE DIRECT BLACK 179	6	4-5	4-5	3-4	3
		DIRECT BLACK 2G DIRECT BLACK 201	4	3-4	3-4	3-4	2



COTTON

0.5%

2%

Product Name
(N.B.)

Fastness Properties

Light	Washing	Perspiration	Hypochlorite	Dischargeability
-------	---------	--------------	--------------	------------------

	DIRECT ORANGE GR DIRECT ORANGE 1	3	3-4	3-4	3	2
	DIRECT RED F DIRECT RED 1	4	3-4	3-4	3	3
	DIRECT RED 4B DIRECT RED 2	3	3-4	3-4	2	2
	DIRECT BORDEAUX BW DIRECT RED 13	3	3-4	3-4	2-3	2
	DIRECT CONGO RED DIRECT RED 28	2	3-4	3-4	1-2	2
	DIRECT BROWN MR DIRECT BROWN 2	3	3-4	3-4	3-4	3
	DIRECT GREEN PLS DIRECT GREEN 1	3	3-4	3-4	3	3
	DIRECT GREEN B DIRECT GREEN 6	3	3	3	2-3	2-3
	DIRECT DIZO BLACK BT DIRECT BLACK 2	4	3	3	3-4	3
	DIRECT BLUE 2B DIRECT BLUE 6	3	3	2-3	3	2-3
	DIRECT BLACK EXTRA CONC DIRECT BLACK 38	3	3	3	4	4



PARSHWANATH
DYESTUFF INDUSTRIES
AN ISO 9001 & 14001 CERTIFIED COMPANY

Manufacturer & Exporter

Reactive Dyes, Acid Dyes, Food Color, Direct Dyes,
Pigment Powder, Pigment Paste & Titanium Dioxide

-
- A** Plot No. I/5617, Phase-2, G.I.D.C., Vatva, Ahmedabad-382445. INDIA
 - P** +91-79-4008 3230, 4008 3231
 - M** +91 990 990 3636, 997 987 4744
 - E** inquiry@parshwadyes.com, sonal.modi@parshwadyes.com
 - W** www.parshwadyes.com